

Typical Properties

	TARGET VALUE	TOLERANCE	STANDARD
Basis Weight (g/m²)	710	± 40	ISO 536
Moisture (%)	7.5	± 1.5	TAPPI 412
Density (g/cm³)	0.7	± 0.1	
Caliper (mm)	0.93	≥ 0.9	TAPPI 411
Mullen (kPa)²	800	≥ 500	ISO 2759
Brightness (%)	89	≥ 87	ISO 2470
Dirt (ppm)	0	≤ 4	TAPPI 437
Average Fiber Length Weighted (mm)	0.8	± 0.2	TAPPI 271
Fiberization (%)	91	≥ 86	MTS method

OBSERVATIONS

¹ Test climate conditions: 23°C / 50% RG (according to ISO 187). Tolerances: based upon 95% confidence limits, applied to reel average.

In order to verify, reel average shall be based on ⁵ single measurements randomly sampled within the reel.

² EUCAFLUFF has different grades of products with 'softer' and 'harder' rolls at different mullen rates.

Reel Dimensions

	TARGET VALUE	TOLERANCE
Diameter (mm)	1250	± 100
Width	250 and 490	Different lengths may be provided according to clients' needs.
Core (in)	3"	